

# CYCOLOY™ FR RESIN CS9610

REGION ASIA

## DESCRIPTION

CYCOLOY CS9610 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is an excellent flammability, low smoke grade that can be injection molded. This non-chlorinated, non-brominated flame retardant PC/ABS has a UL V0 & 5VB flame rating. CYCOLOY CS9610 resin is an excellent candidate for a wide variety of applications including enclosures in public areas such as transportation.

## TYPICAL PROPERTY VALUES

Revision 20171213

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	64	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	55	%	ASTM D 638
Tensile Modulus, 50 mm/min	2600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	98	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2440	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	62	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.8	%	ISO 527
Tensile Strain, break, 50 mm/min	>45	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	98	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	800	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	72	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	45	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	15	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	45	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	118	°C	ASTM D 648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	124	°C	ISO 306
Vicat Softening Temp, Rate B/120	127	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	106	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	15	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 260°C/5.0 kg	12	cm <sup>3</sup> /10 min	ISO 1133
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating (3)	2	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2	mm	UL 94
NBS Smoke Density, Flaming, Dmax	225	-	ASTM E 662
NBS Smoke Density, Flaming, Ds 1.5 min	40	-	ASTM E 662
NBS Smoke Density, Flaming, Ds 4 min	150	-	ASTM E 662
<b>INJECTION MOLDING</b>			
Drying Temperature	90	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	270 – 300	°C	
Nozzle Temperature	265 – 300	°C	
Front - Zone 3 Temperature	265 – 300	°C	
Middle - Zone 2 Temperature	260 – 300	°C	
Rear - Zone 1 Temperature	260 – 300	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.