

CYCOLAC™ RESIN FR15U

REGION AMERICAS

DESCRIPTION

Flame retardant ABS. Excellent indoor UV properties. Excellent moldability. UL94V-0/5VA rated. Elevated UL RTI rating.

TYPICAL PROPERTY VALUES

Revision 20180327

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	37	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	30	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	17	%	ASTM D 638
Tensile Modulus, 5 mm/min	2060	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	67	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	41	MPa	ISO 527
Tensile Strain, break, 50 mm/min	21.9	%	ISO 527
Tensile Modulus, 1 mm/min	2210	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	63	MPa	ISO 178
Flexural Modulus, 2 mm/min	2260	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	213	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	28	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	93	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	86	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	75	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.18E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/50	92	°C	ISO 306
Relative Temp Index, Elec	90	°C	UL 746B
Relative Temp Index, Mech w/impact	85	°C	UL 746B
Relative Temp Index, Mech w/o impact	90	°C	UL 746B
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 230°C/3.8 kgf	3.3	g/10 min	ASTM D 1238
Melt Viscosity, 200°C, 1000 sec-1	3200	Poise	ASTM D 3825
Density	1.19	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/5.0 kg	7	g/10 min	ISO 1133
Melt Volume Rate, MVR at 220°C/10.0 kg	40	cm ³ /10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Volume Resistivity	>1.E+14	Ohm-cm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	20	kV/mm	IEC 60243-1
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.49	mm	UL 94
UL Recognized, 94-5VA Rating (3)	2.79	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	205 – 230	°C	
Nozzle Temperature	205 – 230	°C	
Front - Zone 3 Temperature	205 – 220	°C	
Middle - Zone 2 Temperature	200 – 210	°C	
Rear - Zone 1 Temperature	170 – 180	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.