

# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

### Product Information

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

**Delrin® 100ST is a super-toughened, high viscosity acetal homopolymer grade with superior impact resistance. It is designed for highly stressed parts where outstanding toughness is essential.**

General information	Value	Unit	Test Standard
Resin Identification	POM-HI	-	ISO 1043
Part Marking Code	POM-HI	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate	1.7	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Melt mass-flow rate	2	g/10min	ISO 1133
Melt mass-flow rate, Temperature	190	°C	ISO 1133
Melt mass-flow rate, Load	2.16	kg	ISO 1133
Moulding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.1	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	1400	MPa	ISO 527-1/-2
Yield stress	41	MPa	ISO 527-1/-2
Yield strain	30	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural Modulus	1100	MPa	ISO 178
Flexural Stress at 3.5%	34	MPa	ISO 178
Poisson's ratio	0.43	-	ISO 527-1/-2
Tensile creep modulus			ISO 899-1
1h	1100	MPa	
1000h	550	MPa	
Charpy impact strength			ISO 179/1eU
23°C	N	kJ/m <sup>2</sup>	
-30°C	N	kJ/m <sup>2</sup>	
Charpy notched impact strength			ISO 179/1eA
23°C	90	kJ/m <sup>2</sup>	
-30°C	18	kJ/m <sup>2</sup>	
Izod notched impact strength			ISO 180/1A
23°C	90	kJ/m <sup>2</sup>	
-40°C	20	kJ/m <sup>2</sup>	
Hardness, Rockwell, M-scale	58	-	ISO 2039-2
Hardness, Rockwell, R-scale	105	-	ISO 2039-2
Coefficient of sliding friction, 1h against itself	0.32	-	ASTM 1894
Specific wear rate, against itself	60	E-6 mm <sup>3</sup> /Nm	ASTM 1894
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-35	°C	ISO 11357-1/-2
Temp. of deflection under load			ISO 75-1/-2
1.8 MPa	60	°C	
0.45 MPa	100	°C	
Vicat softening temperature, 50°C/h, 10N	170	°C	ISO 306
Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	140	E-6/K	ISO 11359-1/-2

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11



# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

Eff. thermal diffusivity	6E-8	m <sup>2</sup> /s	-
RTI, electrical			UL 746B
1.5mm	105	°C	
3mm	105	°C	
RTI, impact			UL 746B
1.5mm	85	°C	
3mm	85	°C	
RTI, strength			UL 746B
1.5mm	85	°C	
3mm	85	°C	
<b>Flammability</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Burning Behav. at 1.5mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	UL	-	UL 94
Glow Wire Flammability Index			IEC 60695-2-12
1mm	550	°C	
2mm	550	°C	
3mm	550	°C	
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	41	mm/min	ISO 3795 (FMVSS 302)
<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Relative permittivity			IEC 62631-2-1
100Hz	4.4	-	
1MHz	3.8	-	
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption, 2mm	0.35	%	Sim. to ISO 62
Water absorption, 2mm	0.9	%	Sim. to ISO 62
Density	1340	kg/m <sup>3</sup>	ISO 1183
Density of melt	1140	kg/m <sup>3</sup>	-
<b>VDA Properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Emissions	<8	mg/kg	VDA 275
1:			
<b>Injection</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Recommended	yes	-	-
Drying Temperature	≥80	°C	-
Drying Time, Dehumidified Dryer	4 - 8	h	-
Processing Moisture Content	≤0.05	%	-
Melt Temperature Optimum	205	°C	-
Min. melt temperature	200	°C	-
Max. melt temperature	210	°C	-
Mold Temperature Optimum	50	°C	-
Min. mould temperature	40	°C	-
Max. mould temperature	60	°C	-
Hold pressure range	60 - 80	MPa	-
Hold pressure time	7.5	s/mm	-
Annealing time, optional	30	min/mm	-
Annealing temperature	160	°C	-
<b>Extrusion</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Temperature	75 - 85	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.05	%	-
Melt Temperature Optimum	200	°C	-
Melt Temperature Range	195 - 205	°C	-

Revised: 2018-03-23

Page: 2 of 10

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

### Characteristics

Processing	<ul style="list-style-type: none"><li>• Injection Moulding</li><li>• Profile Extrusion</li></ul>	<ul style="list-style-type: none"><li>• Sheet Extrusion</li><li>• Other Extrusion</li></ul>
Delivery form	<ul style="list-style-type: none"><li>• Pellets</li></ul>	
Additives	<ul style="list-style-type: none"><li>• Lubricants</li></ul>	<ul style="list-style-type: none"><li>• Release agent</li></ul>
Regional Availability	<ul style="list-style-type: none"><li>• North America</li><li>• Europe</li></ul>	<ul style="list-style-type: none"><li>• Asia Pacific</li><li>• South and Central America</li><li>• Near East/Africa</li><li>• Global</li></ul>

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11




# DuPont™ Delrin® 100ST NC010


## ACETAL RESIN

### Diagrams

#### Viscosity-shear rate




#### Shearstress-shear rate




# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

### Dynamic Shear modulus-temperature




### Dynamic Tensile modulus-temperature



# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

Stress-strain



Revised: 2018-03-23

Page: 6 of 10

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

Secant modulus-strain



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**


Tel: +41 22 717 51 11



# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

Stress-strain (isochronous) 23 °C



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11







# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

Creep modulus-time 23 °C



Specific volume-temperature (pvT)



Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hyrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**

Tel: +41 22 717 51 11



# DuPont™ Delrin® 100ST NC010

## ACETAL RESIN

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11

