

PP

Homo PP for special BOPP Film

▶ HU300

● Description

HU300 is a new class of high crystallinity homo polypropylene with extremely high stiffness and excellent heat resistance. HU300 is designed for the production of BOPP films

● Characteristics

- ▶ Superior mechanical properties;
 - HU300 is suitable for replacement of PET
- ▶ Excellent thermal stability ;
 - Stable thermal shrinkage at high temperature
- ▶ High melting temperature of BOPP Film : 173^oC

● Physical Properties

Typical Properties	Method (ASTM)	Unit	HU300
Melt flow index	D1238	g/10min	3.0
Density	D1505	g/cm ³	0.91
Tensile strength at yield	D638	kg/cm ²	420
Elongation at break	D638	%	400
Flexural modulus	D790	kg/cm ²	20,000
Izod impact strength 23 °C	D256	kgcm/cm	3.0
Rockwell hardness	D785	R-scale	100
Heat distortion temp.	D648	°C	117

* Data shown above are representative values for reference purposes only, and not to be construed as specifications.

● **BOPP Film Properties**

Typical Properties	Method (ASTM)	Unit	HU300	Conv.PP
Thickness		um	30	30
Tensile strength	MD	kg/cm ²	1,500	1,000
	TD		2,800	2,600
Tensile Modulus	MD	kg/cm ²	23,000	18,000
	TD		35,000	29,000

Data performed by or on behalf of Hanwha Total

● **Food Contact Application**

- ▶ Hanwha Total HU300 meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

● **Contacts**

▶ **Product Information & Technical Services**

Disclaimer

This www.cn-plas.com document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE

GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.