

# LEXAN<sup>TM</sup> FR RESINS LUX9616G

REGION EUROPE

## DESCRIPTION

LEXAN LUX9616G is an injection moldable polycarbonate (PC) with an MVR (300°C/1.2kg) 7. It contains non-brominated, non-chlorinated flame retardant systems with UL-94 V0@1.5mm rating. This UV stabilized grade has a diffusion effect and thin wall FR performance providing good color stability under heat exposure.

## TYPICAL PROPERTY VALUES

Revision 20190424

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Hardness, Rockwell R	118	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	62	MPa	ISO 527
Tensile Stress, break, 50 mm/min	58	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	77	%	ISO 527
Tensile Modulus, 1 mm/min	2230	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	94	MPa	ISO 178
Flexural Modulus, 2 mm/min	2250	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	450	J/m	ASTM D 256
Multiaxial Impact	130	J	ISO 6603
Izod Impact, unnotched 80°10*3 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80°10*3 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80°10*3 +23°C	65	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80°10*3 -30°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10*3 sp=62mm	68	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10*3 sp=62mm	12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
CTE, -40°C to 40°C, flow	6.8E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.7E-05	1/°C	ASTM E 831
Specific Heat	1.26	J/g·°C	ASTM C 351
Thermal Conductivity	0.2	W/m·°C	ASTM C177
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10*4 sp=64mm	125	°C	ISO 75/Af
Relative Temp Index, Elec	125	°C	UL 746B
Relative Temp Index, Mech w/impact	115	°C	UL 746B
Relative Temp Index, Mech w/o impact	125	°C	UL 746B
<b>PHYSICAL</b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Density	1.2	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	7	cm <sup>3</sup> /10 min	ISO 1133
<b>OPTICAL</b>			
Refractive Index	1.586	-	ISO 489
<b>ELECTRICAL</b>			
Dielectric Strength, in air, 3.2 mm	15	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D 150
Relative Permittivity, 1 MHz	2.96	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D 150
Dissipation Factor, 1 MHz	0.01	-	ASTM D 150
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-2 Flame Class Rating	0.3	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
Glow Wire Flammability Index 750°C, passes at	0.8	mm	IEC 60695-2-12
Glow Wire Flammability Index 850°C, passes at	1.5	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	850	°C	IEC 60695-2-13
UV-light, water exposure/immersion	F2	-	UL 746C
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	270 – 290	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.