

LNPTM LUBRICOMPTM COMPOUND UX05051

UFL-4026 A FR HS HW

DESCRIPTION

Internally lubricated Polyphthalamide compound, containing Glass Fiber and PTFE. Added features include Heat Stabilized, Flame Retardant and Hot Water Moldable

TYPICAL PROPERTY VALUES

Revision 20200903

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break, 5 mm/min	138	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1	%	ISO 527
Tensile Modulus, 1 mm/min	12100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	188	MPa	ISO 178
Flexural Modulus, 2 mm/min	10700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	2.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.2E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	273	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	140	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	140	°C	UL 746B
PHYSICAL			
Density	1.76	g/cm ³	ISO 1183
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥0.4	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥0.8	mm	UL 746A
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E45329-101949148	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	305 – 315	°C	
Front - Zone 3 Temperature	305 – 320	°C	
Middle - Zone 2 Temperature	305 – 320	°C	
Rear - Zone 1 Temperature	305 – 320	°C	
Mold Temperature	95 – 120	°C	
Back Pressure	0.3 – 0.7	MPa	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	30 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.