



TAIRILITE® PC 樹脂

項目 Property	單位 Unit	試驗方法 Test Method	試驗條件 Test Condition	高透光級
				AC2916
抗張強度 Tensile Strength	kg/cm ² (Mpa)	ASTM D-638 (ISO 527)	23 °C	620 (61)
彎曲強度 Flexural Strength	kg/cm ² (Mpa)	ASTM D-790 (ISO 178)	23 °C	1050 (103)
彎曲模數 Flexural Modulus	kg/cm ² (MPa)	ASTM D-790 (ISO 178)	23 °C	22,200 (2,180)
洛氏硬度 Rockwell Hardness	R-scale	ASTM D-785 (ISO 2039/2)	23 °C	122
Izod 衝擊強度 Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256 (ISO R180)	23 °C 1/8" bar	50 (490)
熱變形溫度 Heat Deflection Temperature	°C	ASTM D-648 (ISO 75/A)	Unannealed 18.6 kg/cm ² (1.8MPa) 1/8" bar	126
熔融指數 Melt Flow Index	g/10 min	ASTM D-1238 (ISO 1133)	300°C×1.2kg	35
比重 Specific Gravity		ASTM D792 (ISO 1183)	23 °C	1.2
透明度 Transmissin	%	ASTM D1003	3.2mm	90.5
霧度 Haze	%	ASTM D-1003	3.2mm	0.3
特性 CHARACTERISTICS	高透光性、高流動			

以上數值係參考 ASTM、ISO 試驗方法所測得，僅供選擇用途品級之參考。

台灣化學纖維股份有限公司-塑膠部
電話: 02-27122211 / 傳真: 02-27131649
地址: 台北市松山區敦化北路 201 號
網址: <https://www.fcc-plastics.com/>



台塑關係企業
FORMOSA PLASTICS GROUP

