

LEXAN™ COPOLYMER EXL1182T

REGION EUROPE

DESCRIPTION

LEXAN EXL1182T polycarbonate (PC) siloxane copolymer resin is a UV stabilized, enhanced release transparent injection molding (IM) grade. This resin offers good low temperature (-20 C) ductility in combination with high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC resins. LEXAN EXL1182T resin is a UV stabilized, enhanced release product available in transparent and opaque colors and may be an excellent candidate for a broad range of applications.

TYPICAL PROPERTY VALUES

Revision 20171116

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	117.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	2260	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	94	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2240	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	56	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.4	%	ISO 527
Tensile Strain, break, 50 mm/min	119.4	%	ISO 527
Tensile Modulus, 1 mm/min	2340	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	89	MPa	ISO 178
Flexural Modulus, 2 mm/min	2140	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	736	J/m	ASTM D 256
Izod Impact, notched, -30°C	618	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	74	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	47	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	24	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	61	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	17	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL			
Vicat Softening Temp, Rate A/50	138	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D 648
CTE, -40°C to 95°C, flow	7.48E-05	1/°C	ASTM E 831
CTE, -40°C to 95°C, xflow	7.64E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	7.48E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.64E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	20	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.24	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	19	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.