

LNP™ THERMOCOMP™ COMPOUND 2X98703

PDX-FP-E-98703
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP 2X98703 is a compound based on ETFE Copolymer resin containint Proprietary Filler(s).

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	101	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	98	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	5.6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	5.9	%	ASTM D 638
Tensile Modulus, 5 mm/min	14180	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	143	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	10600	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	95	MPa	ISO 527
Tensile Stress, break, 5 mm/min	88	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	5.5	%	ISO 527
Tensile Modulus, 1 mm/min	11220	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	135	MPa	ISO 178
Flexural Modulus, 2 mm/min	10440	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	481	J/m	ASTM D 4812
Izod Impact, notched, 23°C	411	J/m	ASTM D 256
Multiaxial Impact	8	J	ISO 6603
Instrumented Impact Total Energy, 23°C	20	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	88	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	34	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	248	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	214	°C	ASTM D 648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	1.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ASTM E 831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	239	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	187	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.73	-	ASTM D 792
Density	1.73	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.01	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.01	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Melt Temperature	315	°C	
Front - Zone 3 Temperature	325 – 340	°C	
Middle - Zone 2 Temperature	300 – 325	°C	
Rear - Zone 1 Temperature	280 – 300	°C	
Mold Temperature	90 – 120	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.