

CYCOLOY™ FR RESIN CX2142ME

REGION EUROPE

DESCRIPTION

CYCOLOY CX2142ME Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is an improved chemical resistant grade that can be injection molded. This non-chlorinated, non-brominated flame retardant PC/ABS has a UL V0 & 5VB flame rating. CYCOLOY CX2142ME resin an excellent candidate for a wide variety of applications including enclosures for hospital equipment.

TYPICAL PROPERTY VALUES

Revision 20171213

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	64	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	90	%	ASTM D 638
Tensile Modulus, 50 mm/min	2900	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2700	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	61	MPa	ISO 527
Tensile Stress, break, 50 mm/min	51	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	100	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	600	J/m	ASTM D 256
Izod Impact, notched, -30°C	120	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	63	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	15	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
THERMAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	102	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	84	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	102	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	84	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	22.5	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	21	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.2	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 275	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	245 – 275	°C	
Middle - Zone 2 Temperature	220 – 265	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	60 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.