

DuPont™ Delrin® FG400MTD BLA079

ACETAL RESIN

Product Information

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® FG400MTD is a metal-filled, medium viscosity acetal copolymer for injection moulding. It is detected in metal detectors. It has been developed for applications in contact with food.

FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from your DuPont representative.

| General information | Value | Unit | Test Standard |
|---|-------------|-------------------|----------------------|
| Resin Identification | POM-MED(Fe) | - | ISO 1043 |
| Part Marking Code | POM-MED(Fe) | - | ISO 11469 |
| Rheological properties | Value | Unit | Test Standard |
| Melt mass-flow rate | 17 | g/10min | ISO 1133 |
| Melt mass-flow rate, Temperature | 190 | °C | ISO 1133 |
| Melt mass-flow rate, Load | 2.16 | kg | ISO 1133 |
| Moulding shrinkage, parallel | 1.7 | % | ISO 294-4, 2577 |
| Moulding shrinkage, normal | 1.6 | % | ISO 294-4, 2577 |
| Mechanical properties | Value | Unit | Test Standard |
| Tensile Modulus | 2800 | MPa | ISO 527-1/-2 |
| Yield stress | 61 | MPa | ISO 527-1/-2 |
| Yield strain | 8 | % | ISO 527-1/-2 |
| Nominal strain at break | 15 | % | ISO 527-1/-2 |
| Flexural Modulus | 2700 | MPa | ISO 178 |
| Charpy impact strength, 23°C | 70 | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 3 | kJ/m ² | ISO 179/1eA |
| Thermal properties | Value | Unit | Test Standard |
| Melting temperature, 10°C/min | 168 | °C | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.8 MPa | 100 | °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion, parallel | 120 | E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, normal | 120 | E-6/K | ISO 11359-1/-2 |
| Flammability | Value | Unit | Test Standard |
| FMVSS Class | B | - | ISO 3795 (FMVSS 302) |
| Burning rate, Thickness 1 mm | <100 | mm/min | ISO 3795 (FMVSS 302) |
| Other properties | Value | Unit | Test Standard |
| Density | 1530 | kg/m ³ | ISO 1183 |
| Injection | Value | Unit | Test Standard |
| Drying Recommended | yes | - | - |
| Drying Temperature | ≥80 | °C | - |
| Drying Time, Dehumidified Dryer | 2 - 4 | h | - |
| Processing Moisture Content | ≤0.2 | % | - |
| Melt Temperature Optimum | 205 | °C | - |
| Min. melt temperature | 200 | °C | - |
| Max. melt temperature | 210 | °C | - |
| Mold Temperature Optimum | 90 | °C | - |
| Min. mould temperature | 80 | °C | - |
| Max. mould temperature | 100 | °C | - |
| Hold pressure range | 80 - 100 | MPa | - |
| Hold pressure time | 8 | s/mm | - |

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Delrin® FG400MTD BLA079

ACETAL RESIN

Characteristics

| | | | |
|-----------------------|----------------------|-----------------------------|--------------------|
| Processing | • Injection Moulding | | |
| Delivery form | • Pellets | | |
| Additives | • Release agent | | |
| Regional Availability | • North America | • Asia Pacific | • Near East/Africa |
| | • Europe | • South and Central America | • Global |

Processing Texts

Injection molding

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11




DuPont™ Delrin® FG400MTD BLA079


ACETAL RESIN

Diagrams

Viscosity-shear rate




Shearstress-shear rate



DuPont™ Delrin® FG400MTD BLA079

ACETAL RESIN

Specific volume-temperature (pvT)



Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

