

VALOXTM RESIN 337

REGION AMERICAS

DESCRIPTION

Low temperature impact PBT. Automotive applications: underhood power distribution boxes and covers.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	39	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.9	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	56	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1790	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	870	J/m	ASTM D 256
Izod Impact, notched, -30°C	801	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	47	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Water Absorption, 24 hours	0.1	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	2.4 – 2.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	2.4 – 2.7	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	12.7	g/10 min	ASTM D 1238
Melt Viscosity	1200	Pa-s	SABIC method
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.013 – 0.025	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.