

# PCP-2605

Polycarbonate compound resin

## General information

### Description

Easy mold release  
Non-brominated, non-chlorinated flame retardant  
Available in opaque color only

### Applications

Multi purpose grade (electric/electronic housings, etc.)

## Typical properties<sup>1</sup>

	Test method	Typical value	Unit	
<b>Physical</b>				
Melt Flow Index, 300°C, 1.2kg	ASTM D1238	-	g/10 min	
Specific Gravity	ASTM D792	1.20		
Mold Shrinkage	ASTM D955	0.5~0.7	%	
<b>Mechanical</b>				
Tensile Strength, yield, 50 mm/min	ASTM D638	620	kg <sub>f</sub> /cm <sup>2</sup>	
Tensile Elongation, break, 50 mm/min	ASTM D638	> 100	%	
Flexural Strength, yield, 10 mm/min	ASTM D790	900	kg <sub>f</sub> /cm <sup>2</sup>	
Flexural Modulus, 10 mm/min	ASTM D790	24,000	kg <sub>f</sub> /cm <sup>2</sup>	
IZOD Impact Strength, notched, 23°C, 1/8"	ASTM D256	60	kg <sub>f</sub> -cm/cm	
	notched, 23°C, 1/4"	ASTM D256	-	kg <sub>f</sub> -cm/cm
	notched, -30°C, 1/8"	ASTM D256	-	kg <sub>f</sub> -cm/cm
<b>Thermal</b>				
Heat Distortion Temp.	4.6 kg <sub>f</sub> /cm <sup>2</sup>	ASTM D648	-	°C
	18.6 kg <sub>f</sub> /cm <sup>2</sup>	ASTM D648	110	°C
Vicat Softening Temp.	Rate B/50	ASTM D1525	-	°C
<b>Flammability</b>				
UL94 V-1	UL94	1.5	mm	
UL94 5VB	UL94	2.0	mm	
UL94 V-0, 5VB	UL94	3.0	mm	

## Notes

ISO 9001, 14001, TS 16949


<sup>1</sup> Typical properties : these are not to be construed as specifications.

# PCP-2605

Polycarbonate compound resin

## Processing guides<sup>1</sup>

	Typical value	Unit
<b>Drying condition</b>		
Drying temperature	100	°C
Drying time	4	hr
Maximum moisture content	0.02	%
<b>Injection molding</b>		
Melt temperature	260 ~ 280	°C
Nozzle temperature	260 ~ 270	°C
Barrel		
Rear zone	260 ~ 280	°C
Middle zone	250 ~ 270	°C
Front zone	240 ~ 260	°C
Hopper temperature	60 ~ 80	°C
Mold temperature	60 ~ 90	°C



## Recycling

Sprues and runners can be reground with virgin resin within the ratio of 20%. Care must be taken to ensure that the regrind is free from impurities and regrind should not be used in applications where impact performance and/or agency compliance are required.

## Notes

ISO 9001, 14001, TS 16949

<sup>1</sup> Processing guides : Typical processing parameters are noted. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, etc.